




Alpine

385, price group 2


Alpine is nice and authentic bouclé woven quality which is a perfect fit for our collection. Softness, volume, and elegance are their characteristics. Alpine combines polyester and polyacrylic yarns, twisted to make a beautiful upholstery fabric. Bouclé yarns are really fun to spin. Made by first creating loose loops around a core yarn, bouclé yarns look marvelous and are a very popular choice in furniture fabrics. This article can be applied widely: perfect for loose covers and easily upholstered on tight-fitted models.



96% Polyester
4% Polyacrylic



Martindale: >75.000



Lightfastness: 5

PRODUCT CHARACTERISTICS

Product group	flatweave
Applications	sofas, beds, chairs with fitted and loose fitting upholstery.
Composition faceside	96%PES 4%PAC
Composition upside	n/a
Bonding	transparent
Statistic code	54079300
Dyeing method	yarn dyed
Available colours	14
Packaging	transparent plastic



DURABILITY SPECIFICATIONS


Test	Test specification	Executed by laboratory:	Unit	Test result		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04. DIN EN ISO 12947-2:2017-03	CTL	cycles	75.000		min. 8.000	min. 16.000	B
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4		min. 3-4	min. 4	B
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min.5	B
	middle colours	CTL	grade	5		min. 4	min.5	B
	dark colours	CTL	grade	5		min. 4	min.5	B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Ignitability (cigarette test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette.	CTL		passed				

PROCESSING SPECIFICATION

Minimum workable width [cm]	± 143							
Roll length [m]	± 30							
Material weight [g/m]	± 715							
Test	Test specification	Executed by laboratory:	Unit	Test result		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1514	717	min. 350	min. 350	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	136,9	176,3	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	1,8	1,6	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	27,4	17,7	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				

All information is based on the data provided by the manufacturer.

CLEANING SPECIFICATIONS

Test	Test specification	Executed by laboratory:	Unit	Test result		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30° C DIN EN	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	-0.4	-2.0	n/a	n/a	A/A
				<p>- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture slightly damp after washing.</p>				