

Mito

463, price group 1

Mito is a flatwoven fabric, laminated with a thick non-woven backing to develop a unique structure that is durable, strong, and suitable, yet soft to the touch. It comes in beautiful light colors and has a luxurious quality that will make you fall in love with it at first sight. Delicate but sustainable, it is perfect for living room furniture, imparting a cozy yet high-quality feeling to the interior.

Faceside: 90% Polyester, 10% Nylon
Backside: 100% Polyester

Martindale: 40.000

Lightfastness: 4-5

PRODUCT CHARACTERISTICS

Product group	chenille flatweave
Applications	sofa's, chairs with fitted and loose fitting upholstery
Composition faceside	90% PES, 10% NY
Composition upside	100% PES
Bonding	non-woven
Statistic code	54075200
Dyeing method	piece dyed
Available colours	14

DURABILITY SPECIFICATIONS

Test	Test specification	Executed by laboratory:	Unit	Test result		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	40.000		min. 8.000	min. 16.000	B
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4		min. 3-4	min. 4	B
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	4		min. 4	min.5	C
	middle colours	CTL	grade	5		min. 4	min.5	B
	dark colours	CTL	grade	5		min. 4	min.5	B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Ignitability (cigarette test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette.	CTL		passed				

PROCESSING SPECIFICATION

Minimum workable width [cm]	± 143
Roll length [m]	± 40
Material weight [g/m]	± 493

Test	Test specification	Executed by laboratory:	Unit	Test result		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1,046	496	min. 350	min. 400	A/B
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	70,3	96,6	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	2,7	2,9	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	n/a	n/a	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				
	Oeko-Tex, product class II	Centexbel		certified				

CLEANING SPECIFICATIONS

Test	Test specification	Executed by laboratory:	Unit	Test result		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30° C DIN EN	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	0,0	-1,2	n/a	n/a	A/A



- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture slightly damp after washing.

All information is based on the data provided by the manufacturer.