

## Addore 256, price group 2

Very soft in appearance this plain velvet fabric has a glamorous feel. Like the name implies this is a fabric you will simply adore. Due to its natural pile appearance the Adore fabric has a shiny quality that gives it a special kind of charm with a slightly silvery effect when exposed to light. As furniture cover this fabric looks and feels beautiful and luxurious.







Lightfastness: 4-5

| PRODUCT CHARACTERISTICS |                                                         |  |  |  |
|-------------------------|---------------------------------------------------------|--|--|--|
| Product group           | polyester velvet knitted                                |  |  |  |
| Applications            | sofa's, chairs with fitted and loose fitting upholstery |  |  |  |
| Composition faceside    | 100% PES                                                |  |  |  |
| Composition upside      | 100% PES                                                |  |  |  |
| Bonding                 | T/C                                                     |  |  |  |
| Statistic code          | 60053700                                                |  |  |  |
| Dyeing method           | piece dyed                                              |  |  |  |
| Available colours       | 8                                                       |  |  |  |



| Test                                   | Test specification                                                                                                                   | Unit                                                                                                                                       | Test result |        |  |  |
|----------------------------------------|--------------------------------------------------------------------------------------------------------------------------------------|--------------------------------------------------------------------------------------------------------------------------------------------|-------------|--------|--|--|
|                                        |                                                                                                                                      |                                                                                                                                            | Dry         | Wet    |  |  |
| Abrasion resistance -<br>yarn breakage | DIN EN ISO 12947-1:2007-04,<br>DIN EN ISO 12947-2:2017-03                                                                            | cycles                                                                                                                                     | 88,000      |        |  |  |
| Pilling                                | DIN EN ISO 12945-2:2000-11.<br>2000 cycles                                                                                           | grade                                                                                                                                      | 5           |        |  |  |
| Colour fastness to light               | DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5                                                                              |                                                                                                                                            |             |        |  |  |
|                                        | light colours                                                                                                                        | grade                                                                                                                                      | 5           |        |  |  |
|                                        | middle colours                                                                                                                       | grade                                                                                                                                      | 5           |        |  |  |
|                                        | dark colours                                                                                                                         | grade                                                                                                                                      | 4-5         |        |  |  |
| Colour fastness to rubbing             | DIN EN ISO 105-X12:2016-11                                                                                                           |                                                                                                                                            |             |        |  |  |
|                                        | light colours                                                                                                                        | grade                                                                                                                                      | 4-5         | 4-5    |  |  |
|                                        | middle colours                                                                                                                       | grade                                                                                                                                      | 4-5         | 4-5    |  |  |
|                                        | dark colours                                                                                                                         | grade                                                                                                                                      | 4-5         | 4-5    |  |  |
| Ignitability<br>(cigarette test)       | BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Sa<br>1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette. | 2 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations:<br>5, 1324. Schedule 4 part 1 Ignition source 0: cigarette. |             | passed |  |  |

| PROCESSING SPECIFICATION    |                            |        |             |      |  |  |
|-----------------------------|----------------------------|--------|-------------|------|--|--|
| Minimum workable width [cm] | ± 138                      |        |             |      |  |  |
| Roll length [m]             | ± 40                       |        |             |      |  |  |
| Material weight [g/m]       | ± 580                      |        |             |      |  |  |
| Test                        | Test specification         | Unit   | Test result |      |  |  |
|                             |                            |        | Warp        | Weft |  |  |
| Tensile strength            | DIN EN ISO 13934-1:2013-08 | Newton | 691         | 583  |  |  |
| Tear growth resistance      | DIN EN ISO 13937-3:2000-06 | Newton | 71,6        | 61,4 |  |  |
| Seam slippage               | DIN EN ISO 13936 2         | mm     | 2,5         | 2,0  |  |  |

## **CLEANING SPECIFICATIONS**











- It is essential to wash the cover inside out and immediately place the cover back to the piece of furniture slightly damp after washing.
- Please note that during washing the damp and dirt prevented treatment will disappear faster.
- Dirt and damp prevention treatment applied.